

A 1

1. (Amended) A method of producing a flaky fine powder, comprising:

adding alkoxysilane and/or silicic acid solution to a dispersion containing a flaky or scaly base and spherical silica particles, and

immobilizing said spherical silica particles on the surface of said ~~said~~ flaky or scaly base by hydrolyzing said alkoxysilane and/or gelling said silicic acid solution,

said flaky or scaly base having a thickness of about 1 μm or less and ~~is~~ ^{being} selected from the group consisting of mica, talc and platelet shaped silica, and said spherical silica particles comprise SiO_2 or a mixture of SiO_2 with one or more of Al_2O_3 , ZrO_2 , MgO , ZnO , CeO_2 or Fe_2O_3 , said spherical silica particles being non-porous and having an average particle size of 0.05-3 μm ,

wherein the permittivity (ϵ) of said dispersion is in the following range:

$$15 \leq \epsilon \leq 80$$

and the ion concentration (N) of the sum of cations and anions in said dispersion satisfies the following conditions:

(a) $200 \text{ ppm} \leq N \leq 5 \cdot 10^4 \text{ ppm}$, when ϵ is 15,

(b) $3 \cdot 10^4 \text{ ppm} \leq N \leq 2 \cdot 10^5 \text{ ppm}$, when ϵ is 80, and

(c) N is in a quadrilateral area formed by A (15, 200), B (15,

5*10⁴), C (80, 2*10⁵) and D (80, 3*10⁴) in the (X,Y) coordinate system with the X axis for the permittivity (ϵ) (-) and the Y axis for the ion concentration (N) (ppm), when $15 \leq \epsilon \leq 80$.

Co.
A4

2. (Amended) A method of producing a flaky fine powder comprising:

(a) dispersing a flaky or scaly base having a thickness of about 1 μ m or less selected from the group consisting of mica, talc and platelet shaped silica, and spherical silica particles comprised of SiO₂ or a mixture of SiO₂ with one or more of Al₂O₃, ZrO₂, MgO, ZnO, CeO₂ or Fe₂O₃, in a dispersion medium comprising an organic solvent and/or water, to adhere said spherical silica particles on the surface of said flaky or scaly base, and

(b) adding alkoxysilane and/or silicic acid solution to the obtained dispersion,

said spherical silica particles being non-porous and having an average particle size of 0.05-3 μ m and immobilized on the surface of said flaky or scaly base by hydrolyzing said alkoxysilane and/or gelling said silicic acid solution,

wherein the permittivity (ϵ) of said dispersion is in the following range[;]:

$$15 \leq \epsilon \leq 80$$

and the ion concentration (N) of the sum of cations and anions in said dispersion satisfies the following conditions:

- cat
A4
- (a) $200 \text{ ppm} \leq N \leq 5 \cdot 10^4 \text{ ppm}$, when ϵ is 15,
- (b) $3 \cdot 10^4 \text{ ppm} \leq N \leq 2 \cdot 10^5 \text{ ppm}$, when ϵ is 80, and
- (c) N is in a quadrilateral area formed by A (15, 200), B (15, $5 \cdot 10^4$), C (80, $2 \cdot 10^5$) and D (80, $3 \cdot 10^4$) in the (X,Y) coordinate system with the X axis for the permittivity (ϵ) (-) and the Y axis for the ion concentration (N) (ppm), when $15 \leq \epsilon \leq 80$.
-

A2

5. (Amended) A method of producing a flaky fine powder comprising:

dispersing (a) a flaky or scaly base having a thickness of about $1 \mu\text{m}$ or less selected from the group consisting of mica, talc and platelet shaped silica, and (b) spherical silica particles comprised of SiO_2 or a mixture of SiO_2 with one or more of Al_2O_3 , ZrO_2 , MgO , ZnO , CeO_2 or Fe_2O_3 , in a dispersion medium, said spherical silica particles being non-porous and having an average particle size of $0.05\text{-}3 \mu\text{m}$,

said spherical silica particles being deposited on a surface of said flaky or scaly base in said dispersion medium, and a flaky, fine powder being obtained by filtering, washing and drying the obtained dispersion,

wherein the permittivity (ϵ) of said dispersion is in the following range:

$$15 \leq \epsilon \leq 80$$

and the ion concentration (N) of the sum of cations and anions of said dispersion satisfies the following conditions,

Cont
A2

$200 \text{ ppm} \leq N \leq 5 \times 10^4 \text{ ppm}$, when ϵ is 15,

$3 \times 10^4 \text{ ppm} \leq N \leq 2 \times 10^5 \text{ ppm}$, when ϵ is 80, and

N is in a quadrilateral area formed by A (15, 200), B (15, 5×10^4), C (80, 2×10^5) and D (80, 3×10^4) in the (X,Y) coordinate system with the X axis for the permittivity (ϵ) (-) and the Y axis for the ion concentration (N) (ppm), when $15 \leq \epsilon \leq 80$.

6. (Amended) The method according to claim 5, further comprising immobilizing said spherical silica particles on the surface of said flaky or scaly base by adding alkoxysilane and/or silicic acid solution to said dispersion.

7. (Amended) The method according to claim 5, further comprising immobilizing said spherical silica particles on said surface of said flaky or scaly base by adding alkoxysilane to said dispersion and hydrolysing said alkoxysilane.

A3

9. (Amended) The method according to claim 5, further comprising immobilizing said spherical silica particles on the surface of said flaky or scaly base by adding silicic acid solution to said dispersion, and gelling said solution.

A4

23. (Amended) A method of producing a flaky fine powder comprising:

A4 hydrolyzing tetraethoxysilane in a dispersion containing mica flakes having a thickness of about 1 μm or less, to thereby precipitate the silica and immobilize said silica on the surface of said mica flakes non-porous spherical silica particles having an average particle size of 0.05-3 μm ,

wherein the permittivity ϵ of said dispersion is in the following range;

$$15 \leq \epsilon < 80$$

and the ion concentration (N) of the sum of cations and anions in said dispersion satisfies the following conditions,

- (a) $200 \text{ ppm} \leq N \leq 5 \cdot 10^4 \text{ ppm}$, when ϵ is 15,
- (b) $3 \cdot 10^4 \text{ ppm} \leq N \leq 2 \cdot 10^5 \text{ ppm}$, when ϵ is 80, and

Cont
AY
(c) N is in a quadrilateral area formed by A (15, 200), B (15, 5×10^4), C (80, 2×10^5) and D (80, 3×10^4) in the (X,Y) coordinate system with the X axis for the permittivity (ϵ) (-) and the Y axis for the ion concentration (N) (ppm), when $15 \leq \epsilon \leq 80$.
